

Shaped Cutting-Grade Inserts with Transitionless Diamond-Enhanced Surface Layer

James E. Boyce,

Halliburton Energy Services, Inc.,

Newcomer Products, Inc., and

U.S. Synthetics, Inc.,

Attorney's Docket No. SC-00-008

Dr. Betty Formby, REG.PAT.AGENT

Shaped Cutting-Grade Inserts with Transitionless Diamond-Enhanced Surface Layer

Cross-Reference to Other Application

5 This application claims priority from 60/223,536 filed
08/04/2000, which is hereby incorporated by reference.

Background and Summary of the Invention

The present invention relates to inserts used in rotary cone drill bits and related drilling tools.

Background: Rotary Drilling

10 Oil wells and gas wells are drilled by a process of rotary drilling. In a conventional drill rig, as seen in **Figure 12** a drill bit **130** is mounted on the end of a drill string **132**, made of many sections of drill pipe, which may be several miles long. At the surface a rotary drive turns the string, including the bit **136** at the bottom of the hole,
15 while drilling fluid (or "mud") is pumped through the string by very powerful pumps **134**. The bit **136** is generally one of two types: either a rotary cone drill bit, such as the one seen in **Figure 10**, or a fixed head bit, such as is seen in **Figure 11**. These bits, which are generally formed of steel, will have structures for cutting or grinding the
20 formation being drilled. One type of cutting or shearing structure is teeth, which are cut out of the steel of the bit body and generally coated with a hardfacing for wear resistance. For cutting or grinding, inserts formed of a harder material such as tungsten carbide are fastened into sockets specially formed within the bit to hold them.

25 When the bit wears out or breaks during drilling, it must be

FOE080" 674E2660

Background: Tungsten Carbide

5 Tungsten carbide is produced in a number of different grades, with different sizes of tungsten particles, different binders, and different percentages of binder present. Generally, the formulations containing a larger percentage of binder are considered tougher (more fracture resistant) and easier to bond to, while a lower percentage of binder gives a harder and more wear resistant insert. Historically, when an overlying layer was to be added, the substrate would have a binder content of at least 13% to provide a good bond to the added layer.

Background: Inserts of Two Carbide Formulations Dispersed in Each Other

15 U.S. Patent 4,956,012, which is owned by Newcomer Products, Inc., (one of the joint assignees) discloses a method of making drilling inserts by mixing nodules of pre-blended, un-sintered metal carbide/binder composites having certain desirable characteristics such as a very high hardness, oxidation resistance or gall resistance, and dispersing these nodules into other pre-blended, un-sintered and pelletized metal carbide/binder compositions having other desirable characteristics such as high toughness, corrosion resistance, or other property. The dispersion of the first composite into the second composite occurs prior to pressing and sintering of the mixture. In this manner, the integrity of the separate grades is maintained, while the properties of the new composite are enhanced.

Background: Layered Insert without Adhesive

25 U.S. Patent 5,594,931, which is owned by Newcomer Products, Inc. (NPI), discloses an insert having a core made of a first grade of

5 cobalt- or nickel-bonded tungsten carbide (typically a relatively tough composition) with a surface layer of a second grade of distinctively different cobalt- or nickel-bonded tungsten carbide (typically a hard, wear-resistant formulation). The bond between these layers is excellent without the need for an adhesive or transition layer.

Harder Inserts Having Seamless Diamond-Enhanced Surface

10 The present application discloses a shaped insert for a drilling tool, such as a drill bit, the insert having a diamond-enhanced layer which is seamlessly bonded over the working surface. Because of the technique used, the diamond-enhanced layer can be bonded to a substrate which contains less than the traditional 13% binder. This means that it is possible to have a harder insert initially and still be able to bond to it a layer which is enhanced with diamonds or other ultra-hard materials. In one embodiment, the substrate is composed of
15 nodules of a harder grade of carbide dispersed within a less hard, more durable matrix of tungsten carbide, over which the layer having a superhard coating is applied. The coating, one embodiment of which contains bare diamonds and carbide, is coated onto a sintered or pre-sintered insert, which is then treated with a high temperature, high
20 pressure process. No transition layer or adherent material is necessary to bond the ultra-hard layer onto the insert.

The disclosed innovations, in various embodiments, provide one or more of at least the following advantages:

- the process is simple;
- 25 ● the bond is strong;
- the performance is increased;
- diamond-enhanced layer gives increased lifetime;
- increased flexibility of deciding toughness/hardness of substrate.

Brief Description of the Drawing

The disclosed inventions will be described with reference to the accompanying drawings, which show important sample embodiments of the invention and which are incorporated in the specification hereof by reference, wherein:

Figure 1 is a photomicrograph of a cross section of a PDC dome insert according to one embodiment of the invention.

Figure 2 is a scanning electron microscope (SEM) photo of the insert of Figure 1 and shows the distribution of the diamonds throughout the coating.

Figure 3 is a further SEM photo of the insert of Figure 1, showing the metallurgical bond at the interface of the coating and carbide substrate.

Figure 4 is a graph of the cobalt profile in one embodiment of the innovative insert.

Figure 5 is an SEM photo of a grade NP32 carbide formulation.

Figure 6 is an SEM photo of a grade N410 carbide formulation.

Figure 7 is an SEM photo of an exemplary composite of the two grades shown in Figure 5 and 6.

Figure 8 is an SEM photo of the interface between the two carbides in the composite of Figure 7.

Figure 9 is a layout of one of the test bits, showing the dome insert locations on the bit pads.

Figure 10 shows a rotary cone drill bit which can use the innovative inserts.

Figure 11 shows a fixed head drill bit which can use the innovative inserts.

Figure 12 shows a drill rig which can use the disclosed insert in

[illegible]

Figure 13 is a flowchart of the process of manufacturing the disclosed insert.

Figure 14 is a table showing the composition of the tungsten
5 carbide grades used in the presently preferred embodiment.

Figure 15 is a table of the relative physical properties of the grades of tungsten carbide used in the body of the disclosed insert.

Detailed Description of the Preferred Embodiments

The numerous innovative teachings of the present application will be described with particular reference to the presently preferred embodiment (by way of example, and not of limitation).

5 Presently Preferred Embodiment

Formation of the disclosed insert will now be discussed with reference to **Figure 13**, which is a flowchart of the process, and to Figures 2-8, which exemplify various aspects of the insert. In step **1410**, the basic insert is formed. This is preferably done using the process which was disclosed in U.S. Patent 4,956,012, which is hereby incorporated by reference. In this process, pellets of tungsten carbide are formed from two different grades of tungsten carbide, one to provide the desired hardness, the other to provide the toughness. In the presently preferred embodiment, the grades are grades NP32 and N410 of Newcomers Products, Inc.'s (NPI), the composition of which is shown in **Figure 14**. Grade NP32 (for hardness) consists of submicron size tungsten carbide particles with 6% cobalt (seen in an scanning electron microscope (SEM) photo in **Figure 5**), while grade N410 (for toughness) consists of 4 micron particles of tungsten carbide with 10% cobalt (seen in **Figure 6**). These pellets are formed by any pelletizing process, such as vibratory pelletizing, wet pelletizing, spray drying, etc. The pellets are gently dry-mixed, using 60% by weight of N410 pellets and 40% of NP32 to form new composite grade 11493. Relative physical properties of these grades are shown in **Figure 15**. The mixed pellets are pressed and pre-sintered at a low temperature which is sufficient to permit handling of the green insert for further processing (step **1420**) of **Figure 13**. Optionally, a full sinter to densify the insert can be performed at this point (step **1425**). **Figure**

00000-00000-00000

Sample and Testing of Diamond-Enhanced Layer

In initial testing of the diamond-enhanced layer, a number of semi-dome inserts were coated and treated. The diamond thickness was around 0.010 inches and the inserts were brazed into three of the five gage pads of a fixed-head bit (above the cutters marked 2, 3, and 5), as seen in **Figure 9**. The bit was run in a well in Tyler, Texas. After the run, the cutters were debrazed and checked. Wear was evident in the center of the cutter, which may have been done during the overdimension grind process that was performed prior to the test. The cutters appeared to have passed the initial tests; other than the wear, the cutters remained intact.

A microcrack was found in one sample, but that may have been a result of the sample preparation process. The cause of the crack is uncertain, as flaking would be an expected result during drilling if test parts have cracked, but no flaking was seen.

A carbon precipitate was noted near the surface of the carbide substrate. It is not yet clear whether this precipitate adds or detracts anything. Intermediate layer of fine grained tungsten carbide at interface (thickness of 15-25 microns) due to NPI process. Diamond-enhanced layer appears well bonded; EDS detection analysis showed no evidence of contamination of the diamond enhanced layer.

1091101 gage insert measurements:

- before pressing: $0.31580 - 0.31595 \times .270 \pm .005$ (uncoated)
- after pressing: $0.31450 - 0.31500 \times .286 \pm .002$
- before and after pressing dimensions do not match A-00010 print, DASH 00 through DASH 04

1091685 surf compact measurements:

- before pressing: $0.25330 - 0.25345 \times .205 \pm .005$ (uncoated)
 - after pressing: $0.25215 - 0.25320 \times .2245 \pm .002$
 - before and after pressing dimensions do not match A-00010 print,
DASH 00 through DASH 04
- 5 - HTHP processing appears to reduce diameter about 0.001" and increase height about 0.010" (not including layer)

Variations in the Substrate

- Although the embodiment described above uses nodules of two different grades of tungsten carbide, this is not necessary. Single
- 10 grades of carbide can be used, with greater diversity in the formulations of the body of the insert. For instance, grade 413 of Newcomer Products, Inc. contains tungsten carbide in the 4 micron range with 13% binder. This is a grade which has been traditionally used for bonding. In contrast, their harder carbide formulations, such as 410
- 15 (4 micron particles, 10% binder), 510 (5 micron particles, 10% binder), or 610 (6 micron particles, 10% binder) would not traditionally be used as the substrate under a bonded layer, but with the disclosed invention, these harder formulations, and others, can now be used.

Variations in Added Layer

- 20 Rather than the bare diamonds disclosed above, encrusted diamonds can also be used. Cubic boron nitride (CBN) can be used in addition to, or instead of, diamond.

Additionally, the coating can be sprayed on for better thickness uniformity. A somewhat greater thickness can be used for the coating.

Variations in Inserts

While the specification has referred to inserts throughout,

carbide component comprises a body portion of carbide and an outer layer which is attached to said body without a transition layer or adherent material and which contains an ultra-hard material.

According to another disclosed class of innovative embodiments, there is provided: A fabrication method for a carbide component, comprising the steps of: forming a body portion comprising tungsten carbide; sintering said body portion sufficiently to permit handling of said body portion for further processing; applying a coating to a working surface of said body portion, said coating comprising an ultra-hard material; after said applying step, subjecting said body portion and said coating to a high-temperature, high-pressure process to form a finished carbide component; installing said finished carbide component in a drilling tool.

The following background publications provide additional detail regarding possible implementations of the disclosed embodiments, and of modifications and variations thereof, and the predictable results of such modifications:

The Rotary Drilling Series, Unit I, Lesson 2: The Bit (fourth edition), published by the Petroleum Extension Service of The University of Texas at Austin in cooperation with the International Association of Drilling Contractors, which is hereby incorporated by reference.

Modifications and Variations

As will be recognized by those skilled in the art, the innovative concepts described in the present application can be modified and varied over a tremendous range of applications, and accordingly the scope of patented subject matter is not limited by any of the specific

exemplary teachings given.

- None of the description in the present application should be read as implying that any particular element, step, or function is an essential element which must be included in the claim scope: THE
- 5 SCOPE OF PATENTED SUBJECT MATTER IS DEFINED ONLY BY THE ALLOWED CLAIMS. Moreover, none of these claims are intended to invoke paragraph six of 35 USC section 112 unless the exact words "means for" are followed by a participle.

102080" 64222550